

Public printing recommendation

Yasin Standard Clear PEBA Clear

MaterialID MAT0263



3DPiceland Labs
Generated with 3DPiceland Engineering Platform v70.0.4
DIRECT-IMPACT-METHODOLOGY - Izod and Charpy
Methodology
2026-10-04 18:12:06

Guidance boundary: values below are shared base-material guidance resolved only through the canonical BaseMaterialId link. They are not manufacturer-, spool- or printer-specific validated settings. Missing fields remain Not recorded.

Overall —	Engineering axes 0/8	Public rank —	MSRP USD/kg 64.16
--------------	-------------------------	------------------	----------------------

Engineering profile

Overall		—
Tensile		—
Impact		—
Izod		—
Charpy		—
Stiffness		—
Consistency		—
Layer adhesion		—

Recommended applications

- Application guidance awaits sufficient measured evidence and approved score references

Measured strengths

- No scored strength is available yet.

Limitations

- No scored limitation can be established from the available evidence.

Engineering trade-offs

- Complete scoring evidence and approved method references are required before assessing an overall balance of properties.

Base-material printing guidance

Guidance	Minimum	Recommended	Maximum	Unit
Nozzle temperature	250	250	250	°C
Bed temperature	90	90	100	°C
Print speed	11	30	30	mm/s
Cooling	65	65	65	%
Guidance	Value			Unit
Cooling guidance	Moderate			
Drying temperature	80			°C
Drying time	12			hours
Enclosure	Recommended			
Printer / G-code reference	PrusaCoreOneL			
Slicer profile reference	Yasin PEBA			

Print workflow checks

- Confirm nozzle temperature, bed temperature, speed, cooling and drying requirements from the manufacturer profile or spool label.
- Print a small validation part before committing to a long, costly or safety-relevant print.
- Orient the part so the governing load does not rely on an unverified or weak engineering axis.
- Layer-adhesion evidence is weak; avoid critical Z-axis loading without additional validation.
- Repeatability is low on the internal scale; run extra validation specimens before relying on the profile.

Decision guidance

- Overall suitability is unavailable until the required measurements and method references are complete.

Stronger same-family alternatives

MaterialID	Material	Manufacturer	Overall	Tensile	Impact	Izod	Charpy
Confirm exact settings against the manufacturer profile, spool label and actual printer/material combination. Results do not replace application-specific validation.							

[Testing methodology](#) · [Download PDF](#)

Flexible Material Testing

Comparative in-house measurements; n = independent specimens. Separate test groups; Overall unchanged.

Method	Result	Condition	Mean	n	SD	CV %	Range	Not reached
eaacea91	Apparent Compressive Stress at 20% Strain (MPa)	10 s hold · 2 mm displacement · cycle 1	4.345	10	0.07	1.602	4.244–4.448	0
eaacea91	Apparent Compressive Stress at 20% Strain (MPa)	30 s hold · 2 mm displacement · cycle 1	4.224	10	0.066	1.57	4.134–4.338	0
eaacea91	Compression Force at 20% Strain (N)	10 s hold · 2 mm displacement · cycle 1	276.4	10	4.427	1.602	270–283	0
eaacea91	Compression Force at 20% Strain (N)	30 s hold · 2 mm displacement · cycle 1	268.7	10	4.218	1.57	263–276	0
eaacea91	Force reduction from 10 s to 30 s at 20% Strain (%)	first compression only · 2 mm displacement	2.785	10	0.327	11.754	2.473–3.546	0
eaacea91	Force retention at 20% Strain (%)	10–30 s · 2 mm displacement · cycle 1	97.215	10	0.327	0.337	96.454–97.527	0
eaacea91	Residual height loss after recovery (%)	20% compression · 30 s compressed hold · 60 s rest · 10 mm initial height · cycle 1	2.8	10	0.125	4.454	2.6–3	0
ed381ba8	Shore A Hardness (Shore A)	10 s reading · 8 mm	92.5	1	—	—	92.5–92.5	0

Method	Result	Condition	Mean	n	SD	CV %	Range	Not reached
eaacea91	Shore A Hardness (Shore A)	10 s reading · 8 mm	91	1	—	—	91–91	0

Shore location statistics

Within each specimen; specimen numbers are local to each test group. SD uses the sample formula. These readings do not increase independent n.

Method	Scale	Condition	Specimen	Readings	Mean	Location SD	Location CV %
ed381ba8	Shore A Hardness	10 s reading · 8 mm	1	5	92.5	0.5	0.541
eaacea91	Shore A Hardness	10 s reading · 8 mm	1	1	91	—	—

reports/printing-recommendations/MAT0263/

Score policy engineering-score-v70-1: Overall requires tensile, stiffness, consistency, layer adhesion and the Izod/Charpy impact family, each with equal weight. Both impact methods and configured versioned references are required. Missing results and unconfigured scores remain n/a. Legacy Impact is historical only; thermal remains separate. Engineering-axis counts describe displayed evidence, not Overall completeness.

